


**Technical specifications – technische specificaties**  
**Spécifications techniques – technische Daten**

# FE 312



<b>Pile content</b>	65% PE & 35% PP (C-shape)
Poolmateriaal	
Composition du velours	
Polmateriaal	
<b>Manufacturing process</b>	Tufting – 5/16 ″
Fabricagemethode	Getuft
Méthode de fabrication	Tuftée
Herstellungsverfahren	Getuftet
<b>Primary backing</b>	Woven PP, UV stabilized
Tuftdoek	Geweven PP
Support	Tissé PP
Trägermaterial	PP Gewebe
<b>Secondary backing</b>	SBR Latex
Rug	
Dossier	
Rückenausrüstung	
<b>Number of stitches</b>	± 18.900 /m2
Aantal steken	
Nombre de points	
Noppenzahl	
<b>Pile height</b>	± 30 mm
Poolhoogte	
Hauteur du velours	
Polhöhe	

<b>Total height</b>	± 32 mm
Totale hoogte	
Épaisseur totale	
Gesamthöhe	
<b>Pile weight</b>	± 1.450 g/m2
Poolinzetgewicht	
Poids du velours	
Poleinsatzgewicht	
<b>Total weight</b>	± 2.335 g/m2
Totaal gewicht	
Poids total	
Gesamtgewicht	
<b>UV-stability</b>	> 6.000 hours (DIN 53387)
UV-stabiliteit	> 6.000 uren
Stabilité à la radiation UV	> 6.000 heures
UV-Stabilität	> 6.000 Stunden
<b>Width</b>	1-2-3-4-5m
Breedte	
Largeur	
Breite	

For cleaning instructions, maintenance & warranty / Voor reinigen, onderhouden & garantie / Conseils d'entretien, d'installation & garantie / Gebrauchsanweisung, Installation & Garantie : **www.feelds.eu**